




DURA-CORE™ II 5052 Aluminum Honeycomb

June 2003
English Units

Description

DURA-CORE II 5052 aluminum honeycomb provides the aerospace and commercial markets with a high degree of flexibility in solving lightweight structural design challenges.

Prior to bonding, the foil is cleaned and treated using a proprietary chemical conversion coating. The resulting honeycomb exhibits excellent corrosion resistance in hostile environments, especially salt fog. Typical weight loss after 30 days in salt fog (using ASTM B-117) is 15 mg/ft² (161.4 mg/m²), while MIL-C-7438 allows up to 125 mg/ft² (1345.0 mg/m²).



We produce a broad range of cell sizes and densities, assuring that the correct product will be available for your application. When combined with our ability to custom-manufacture specific core types, plus our Special Processing capabilities, we can ship you drop-in core details in any shape, size, density or contour that you need.

For lightweight applications requiring excellent mechanical strength and excellent corrosion resistance at a good value, DURA-CORE II 5052 is the best all-around structural core material.

Applications

- Aircraft control surfaces, flooring
- Energy absorbers
- Aircraft engine nacelles
- RF and EMI shielding
- Advanced sporting equipment
- Space & satellite components
- Air and light directionalization
- Other high-performance applications

Features

- Excellent strength-to-weight ratio
- Corrosion resistant
- Elevated temperature performance to 350° F/177° C
- Fire and fungus resistant
- Broad range of cell sizes
- Easily machined and formed
- Resistant to hostile environments
- Complies with MIL-C-7438 and many other aerospace specifications

Availability

- Unexpanded blocks
- Unexpanded slices
- Expanded sheets
- Pieces cut to size

DURA-CORE II 5052 aluminum honeycomb is available with cell perforations to facilitate venting. Custom dimensions, cell sizes, tolerances and mechanical properties are also available.

How to Order

When ordering, please specify DURA-CORE II 5052 using the following format:

Example: DUR - 5052 - 3.1 - 3/16 - N - E, where

Product	Alloy	Density	Cell Size	Perforated or Non-Perforated	Expanded or Unexpanded
DUR	5052	3.1	3/16	P or N	E or U

Available Dimensions

	Standard		Maximum		Tolerance	
	inches	mm	inches	mm	inches	mm
Ribbon (L)	48	1219	100	2540	+2.0 / -0.0	+50.8 / -0.0
Transverse (W)	96	2438	144	3658	+4.0 / -0.0	+101.6 / -0.0
Thickness (T)			35	889		
	up to 4 inches (102mm) T				±0.005	±0.127
	over 4 inches (102mm) T				±0.062	±1.575
Density	see mechanical characteristics chart				±10%	
Cell Size	see mechanical characteristics chart				±10%	

Alcore gives no warranties, expressed, implied or statutory, or otherwise, as to the description, quality, fitness, capacity, or any other matter, of the properties described. The data given represents typical values to be expected. Through additional testing of each lot it is possible to verify that the product exceeds the tabulated values. It is recommended, however, that prospective users evaluate the materials to determine their suitability for the users' specific requirements. Values are given on the condition that the user assumes all risk and that responsibility for any loss or damage caused by or resulting from the use of such information is disclaimed by Alcore.

Alcore
Lakeside Business Park
1502 Quarry Drive
Edgewood, MD 21040 USA
Tel: +1 (410) 676-7100
Fax: +1 (410) 676-7200
Email: sales@alcore.com
www.alcore.com
www.mcgillcorp.com

Alcore Brigantine
Route de l'Aviation
64600 Anglet France
Tel: +33 (0)5 59 41 25 25
Fax: +33 (0)5 59 41 25 00
Email: sales@alcorebrigantine.fr
www.mcgillcorp.com/alcore_brigantine



Mechanical Characteristics (Typical Values - US units)									
lbs/ft ³ - inches - inches	Stabilized Compressive Strength		Crush Strength	Shear Strength				Shear Modulus	
	psi		psi	psi				ksi	
				L		W		L	W
	75° F	350° F	75° F	75° F	350° F	75° F	350° F	75° F	
3.1 - 1/8 - .0007	305	200	145	215	145	132	90	32	16
4.5 - 1/8 - .0010	580	380	270	345	240	225	150	51	25
6.1 - 1/8 - .0015	1030	660	450	565	400	345	220	77	37
8.1 - 1/8 - .0020	1575	1075	760	810	575	540	310	112	50
10.0 - 1/8 - .0025	1875	1300	1070	1075	810	610	415	140	60
12.0 - 1/8 - .0030	2920	1550	1400	1955*	1300*	950*	440	160	75
2.6 - 5/32 - .0007	245	150	105	170	110	102	80	24	12
3.8 - 5/32 - .0010	415	280	210	275	200	168	140	41	20
5.3 - 5/32 - .0015	730	500	340	425	340	275	200	64	31
6.9 - 5/32 - .0020	1140	780	570	595	500	380	275	91	42
8.4 - 5/32 - .0025	1615	1150	800	770	590	480	330	116	51
2.0 - 3/16 - .0007	180	100	70	122	80	71	65	17	9
3.1 - 3/16 - .0010	340	200	145	215	145	128	90	32	16
4.4 - 3/16 - .0015	555	375	270	335	235	220	145	50	24
5.7 - 3/16 - .0020	870	600	410	465	380	305	200	70	34
6.9 - 3/16 - .0025	1185	780	570	600	500	380	275	91	42
8.1 - 3/16 - .0030	1735	1075	760	735	575	490	310	112	50
1.6 - 1/4 - .0007	102	70	50	88	60	51	35	13	6
2.3 - 1/4 - .0010	215	125	85	145	90	88	70	21	11
3.4 - 1/4 - .0015	375	235	160	235	160	145	100	35	18
4.3 - 1/4 - .0020	545	365	250	325	235	205	140	48	24
5.2 - 1/4 - .0025	770	500	330	415	330	270	160	62	31
6.0 - 1/4 - .0030	1110	650	430	535	390	350	210	75	36
7.9 - 1/4 - .0040	1505	1025	720	710	550	450	300	108	49
1.0 - 3/8 - .0007	56	25	25	46	30	31	30	7	3
1.6 - 3/8 - .0010	98	70	50	88	60	51	35	13	6
2.3 - 3/8 - .0015	205	125	85	140	90	82	70	21	11
3.0 - 3/8 - .0020	315	190	135	205	140	128	85	30	15
3.7 - 3/8 - .0025	415	265	200	255	190	165	105	40	20
4.2 - 3/8 - .0030	565	340	240	315	230	205	130	47	23
5.4 - 3/8 - .0040	810	540	360	435	355	285	180	66	32
6.5 - 3/8 - .0050	1015	750	510	555	440	360	265	83	40
2.6 - 1/2 - .0025	200	150	105	150	110	88	80	24	12
3.0 - 1/2 - .0030	250	190	135	180	140	106	85	30	15
4.0 - 1/2 - .0040	400	320	220	290	220	170	120	44	22
0.8 - 3/4 - .0010	23	20	15	25	25	19	25	5	2
1.8 - 3/4 - .0025	100	90	60	90	70	50	40	15	7
2.1 - 3/4 - .0030	131	105	75	105	85	60	75	18	9
3.0 - 3/4 - .0040	250	190	135	180	140	105	85	30	15
4.2 - 3/4 - .0060	450	340	240	320	230	190	130	47	23

For minimum values, please see MIL-C-7438.

* Beam Shear

