



Gillfloor™ 5007C Panel

June 2005

Description

Gillfloor 5007C is an aircraft sandwich panel made from polyester fiberglass facings fused to end grain balsa wood core. This configuration has thicker, more abrasion resistant facings than 5007B or 5007A.

Applications

Flooring in cargo compartment or other high abuse areas.

Features

- Thick, abrasion, and impact resistant facings.
- Durable performance in cargo compartments..
- High impact facings
- Service temperature range: -65F to 180F.

Specifications

- FAR 25.855 – 12 second vertical and 45° flammability requirements.
- FAR 25.853 – 60 second vertical flammability requirement.

Construction

Adhesive: Modified, fire resistant polyester.

Core: 9 pcf balsa wood.

Facings: Gillfab 1074 with mat overlay.

Availability

Thickness: Per customer specification, from .25" up.

Size: Standard size is 48" x 144". Sizes up to 72" x 168" are available on special order.

Facings: Top - .03", .04" or .045" thick.

Bottom: .025", .030", .035" or .040" thick.

Standard Tolerances

Thickness: +/- .020"

Length: -0, +0.5"

Width: -0, +0.5"



Alternative Gill Products

Product Number	Difference
Gillfloor 5007B	Lighter version for passenger flooring.
Gillfab 5242	Fiberglass cloth bonded to aluminum top skin (not as durable as 5007C but lighter).

TYPICAL PROPERTIES OF GILLFLOOR 5007C
 Based on 0.4" Thick Panel with 0.045"/0.030" Thick Facings
 and 0.325" Thick End-Grain Balsa Core at 9.0 pcf Nominal Density
 Typical Properties

Property	Test Method	Unit	Measurement
Weight	ASTM C29	lb/sq ft (kg/sq m)	1.09 (5.3)
Thickness	ASTM C366	inch (mm)	0.400 (10.2)
Long Beam Flexural Ultimate Load	AMS-STD-401	lb (N)	431 (1917)
Deflectin @ 100 lbs load		ksi (MPa)	22.0 (151.0)
Facing Stress	AMS-STD-401	inch (mm)	0.629 (16.0)
Flatwise Compression	AMS-STD-401	lb/sq in (MPa)	1,982 (13.7)
Flatwise Tensil	AMS-STD-401	lb/sq in (MPa)	644 (4.4)
Insert Shear, Note 1	BMS 4-17	lb (N)	1,028 (4573)
Impact Strength	ASTM 3029	in-lb (N-m)	84 (9.5)
Flammability - 60 Second Vertical Self-Extinguishing Time	FAR Part 25, Appendix F, Part I	second	0
Burn Length		inch (mm)	0.6 (15.2)
Drip Extinguishing Time		second	0
Flammability - 45 Degree Self-Extinguishing Time	FAR Part 25, Appendix F, Part I	second	0
Afterglow		second	0
Penetration		----	None

Note 1: Shurlok Insert 5107-A3 used in test.

M.C. Gill Corporation gives no warranties, expressed, implied or statutory, or otherwise, as to the description, quality, fitness, capacity, or any other matter, of the properties described. The data given represents minimum values to be expected. Through additional testing of each lot it is possible to verify that the product exceeds the tabulated values. It is recommended, however, that prospective users evaluate the materials to determine their suitability for the users' specific requirements. Values are given on the condition that the user assumes all risk and that responsibility for any loss or damage caused by or resulting from the use of such information is disclaimed by M.C. Gill Corporation.

M.C. Gill Corp.
 4056 Easy Street
 El Monte, CA 91731-1087 USA
 626-443-4022 info@mcgillcorp.com

M.C. Gill Europe Ltd. - Insoleq
 23 Enterprise Road, Balloo Industrial Estate South
 Bangor Co-Down BT19 7TA, Northern Ireland
 +44 (0) 2891 470073 sales@mcgillcorp.com

www.mcgillcorp.com

© M.C. Gill Corporation. All rights reserved.

